

TECHNICAL DATA SHEET

FORTIS PRIME820

2 PART EPOXY, ADHESION ENHANCING PRIMER

DESCRIPTION: FORTIS PRIME820 is a two - component epoxy primer formulated to achieve maximum adhesion to porous, mineral and polymer substrates. This product exhibits both organic and inorganic reactivity, allowing the epoxy to chemically react with inorganic substrates, giving enhanced adhesion characteristics.

USES: Priming concrete, ceramics, glass and timber.

COLOUR: Clear

PACK SIZE: 5L kit

FEATURES: Excellent substrate wetting characteristics.
Extended pot life with relatively short film cure time.
Chemically bonds to siliceous and most polar compounds.
Cures well in humid and cold conditions.

SURFACE PREPARATION CONCRETE-

1. Contaminated surfaces should be cleaned with a suitable solvent to remove organic soil and rinsed with clean water.
2. Captive abrasive blast for best results.
3. Alternatively, proceed as follows:
 - (a) Old concrete, where the surface has aged, should be planed or ground to remove the degraded layer.
 - (b) New surfaces (minimum 21 days) should be well etched to remove surface laitance with suitable cleaner, or 10-15% hydrochloric acid solution (commercial hydrochloric acid is supplied at 33%). Properly prepared surfaces should be similar in texture to 80grit sandpaper.
4. Thoroughly wash with clean water to remove reaction by-products and scrub to remove loosened materials. Water – Blasting
5. Allow surfaces to dry.

CERAMICS AND GLASS-

1. Clean contaminated surface with a suitable solvent and wash off residue with clean water.
2. Etch glass or glazed ceramics using either 10% hydrofluoric acid or light sandblasting to produce a matted gloss-free surface.

FORTIS

ADHESIVES & COATINGS

PREVIOUSLY COATED SURFACES-

Remove contaminants by using appropriate cleaners before sanding to provide a keyed surface. Selection of cleaner depends on nature of contaminants, and could include solvent, sugar soap, industrial detergents or cleaners, alkaline cleaners or solvents.

APPLICATION: Thoroughly mix Part A and Part B. Apply to dry substrates, using a short nap roller, wetting out the surface thoroughly and ensuring a continuous film is formed. Porous substrates may require several wet on wet applications with the first coat thinned up to 20% with suitable solvent to aid penetration.

TECHNICAL DATA:

Mix Ratio: 4 parts Part A to 1 part, Part B by Volume
4.55 parts Part A to 1 part, Part B by Weight

Coverage Rate: 6m²/L at 150 microns

Dry Time @ 20°C: 2-4 hours

Recoat Time: 8 - 48 hours

Shelf Life: One year in closed container.

CAUTION: The cure of epoxy products can be affected by moisture, which reacts with the Part B to give a surface "bloom". This blooming can give a permanent loss of gloss, less than normal chemical and physical resistance at the surface, and affect inter-coat adhesion if over-coated. Take all reasonable steps to minimize the risk of water, moisture, or excessive humidity exposure during the cure period (which may be several days in cold temperatures).

SAFETY DATA Please refer to Fortis Safety Data Sheet for Fortis COAT823. Fortis COAT823 is safe if good working practices and proper application equipment is used. Caution should be taken as the material is corrosive. Good industrial hygiene should be observed at all times. Wear suitable protective clothing, impervious gloves, eye and face protection, including suitable breathing protection, such as an air-supplied respirator or organic canister mask. Avoid contact with exposed skin.

Disclaimer

Fortis products should be used in accordance with the information contained here. Each user should read and consider this information carefully in the context of how the products will be handled and used in the workplace including in conjunction with other products. While the information contained here is to the best of our knowledge at the date of publication, Fortis makes no representation about the accuracy of the information. If you need clarification or more information, you should contact Fortis Adhesives & Coatings office directly. Fortis products are sold without express or implied warranties, other than as provided by statute, and subject to our standard terms and conditions

F O R T I S

A D H E S I V E S & C O A T I N G S

(provided to customers and available on request). Subject to our standard terms and conditions, and any statutory provisions, Fortis accepts no responsibility (including in negligence) for loss or damage of any nature resulting from the use of Fortis Adhesives & Coatings products or reliance upon the information contained here